



Shijiazhuang Gezi Screen Mesh C

ADD: Room 701, A Unit, Lecheng Business Building, Qiaoxi district, Shijiazhuang

Tel: 8631169016254

Email: sales@geziexport.com

www.screenmeshchina.com www.geziexport.com

Polyester Screen Printing Mesh

Model	Specification (/cm)	Mesh count (mesh/inch)	Thread Diameter (um)	Mesh opening (um)	Open Area (%)	Thickness (um)
PET7/1068	7	18	350	1068	56	693
PET8/941	8	20	300	941	57	594
PET10/743	10	25	250	743	55	495
PET12/686	12	30	140	686	68	277
PET12/578	12	30	250	578	48	495
PET14/489	14	36	200	489	50	340
PET15/443	15	38	200	443	47	340
PET16/461	16	40	140	461	58	238
PET16/404	16	40	200	404	44	340
PET16/356	16	40	250	356	34	425
PET18/385	18	45	150	385	51	255
PET18/357	18	45	180	357	44	306
PET20/399	20	50	80	399	69	136
PET20/380	20	50	100	380	62	170
PET20/333	20	50	150	333	47	255
PET20/304	20	50	180	304	39	306
PET21/319	21	54	140	319	48	238
PET22/356	22	56	80	356	66	136
PET24/320	24	60	80	320	63	136
PET24/301	24	60	100	301	56	170
PET24/282	24	60	120	282	49	204
PET24/263	24	60	140	263	42	238
PET24/253	24	60	150	253	39	255
PET28/263	28	70	80	263	58	136
PET28/244	28	70	100	244	50	170
PET29/214	29	74	120	214	41	204
PET30/203	30	76	120	203	39	204
PET32/236	32	80	64	236	61	109

PET32/221	32	80	80	221	53	136
PET32/202	32	80	100	202	44	170
PET32/183	32	80	120	183	36	204
PET34/184	34	86	100	184	42	170
PET36/188	36	90	80	188	49	136
PET36/178	36	90	90	178	44	153
PET36/169	36	90	100	169	39	170
PET39/191	39	99	55	191	60	94
PET39/183	39	99	64	183	54	109
PET39/176	39	99	71	176	50	121
PET39/168	39	99	80	168	45	136
PET39/149	39	99	100	149	35	170
PET43/160	43	110	64	160	51	109
PET43/145	43	110	80	145	41	136
PET47/150	47	120	55	150	53	94
PET47/141	47	120	64	141	47	109
PET47/135	47	120	71	135	42	121
PET51/134	51	130	55	134	50	94
PET51/119	51	130	71	119	39	121
PET53/127	53	135	55	127	48	94
PET53/118	53	135	64	118	42	109
PET53/112	53	135	71	112	37	121
PET55/102	55	140	71	105	35	121
PET56/117	56	142	55	117	45	94
PET56/109	56	142	64	109	38	109
PET59/109	59	150	55	109	42	94
PET59/100	59	150	64	100	36	109
PET61/103	61	155	55	103	41	94
PET61/95	61	155	64	95	34	109
PET64/96	64	163	55	96	39	94
PET64/88	64	163	64	88	32	109
PET68/97	68	173	55	87	36	94
PET68/79	68	173	64	79	29	109
PET72/89	72	183	45	89	42	77
PET7/86	72	183	48	86	40	82
PET72/80	72	183	55	80	34	94
PET77/71	77	195	55	71	31	94
PET80/76	80	200	45	76	38	77
PET80/73	80	200	48	73	35	82
PET90/68	90	230	40	68	38	68
PET90/63	90	230	45	63	33	77
PET90/60	90	230	48	60	28	82
PET100/51	100	254	40	51	30	85

PET110/48	110	280	34	48	33	58
PET110/43	110	280	40	43	26	68
PET120/44	120	305	31	44	33	53
PET120/42	120	305	34	42	29	58
PET120/37	120	305	40	37	18	68
PET130/31	130	330	40	31	17	68
PET130/36	130	330	34	36	26	58
PET140/34	140	350	31	34	25	53
PET140/32	140	350	34	32	19	58
PET150/34	150	380	27	34	30	46
PET150/31	150	380	30	31	23	51
PET150/28	150	380	34	28	16	58
PET165/29	165	420	27	29	22	46
PET165/25	165	420	31	25	16	53
PET180/24	180	457	27	24	15	46

**Remark: The above datas are theoretic, please reference th
if there it differs.**

o., ltd

, Hebei, China, 050000

**Theoretic Ink Volume
(cm³/m²)**

389

338

274

189

239

169

160

139

151

145

131

134

93

105

120

120

114

90

86

95

99

100

100

79

85

83

80

67

73
75
74
71
66
67
66
56
59
61
62
60
55
56
50
51
51
47
47
45
45
45
43
42
41
40
39
38
37
36
35
34
32
32
32
31
29
29
29
26
25
23
26

19
18
18
17
13
12
15
13
11
14
12
9
10
8
7

re actual datas